




**Installation Methods**



Herringbone Ashlar

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see [www.interface.com/disclaimer](http://www.interface.com/disclaimer)

**Collection** World Woven **Product** WW865 **Colour** 8110-004-000 Moorland Warp

**Product Specifications**

Product Number	8110
Product Construction	Tufted Loop Pile
Yarn / Fibre	BCF Nylon Type 6 - 100% Recycled content
Yarn Manufacturer	Aquafil
Colour System	100% Solution Dyed
Soil/Stain Protection	Protekt <sup>2®</sup>
Preservative Protection	Intersept <sup>®</sup>
Tufted Pile Weight	17 oz/yd <sup>2</sup> ±10% 577 g/m <sup>2</sup> ±10%
Machine Gauge	Tapestry
Stitches	38.5/10cm 9.8/in
Pile Thickness	2.5 mm ± 0.5mm
Total Thickness	6 mm ± 0.5mm
Pile Density	10,737 oz/yd <sup>3</sup> ± 10%
Size Description	25cm X 1m
Backing Structure ( <a href="#">Learn more</a> )	GlasBac <sup>®</sup>

**Performance Specifications**

Area of Use	Commercial - Heavy Duty
ACCS	Commercial Extra Heavy Duty & Stairs
Stability - Delaminating	AS/NZS 2111.16 ≥ 50 Newtons ISO2551 ≤ 0.1% ASTM D3936 ≥ 2.5lbs/in
Stability - Dimensional Stability	ISO 2551 ≤ 0.1% ISO 2551 ≤ 0.2%
Stability - Tuft Bind	ASTM D1335 ≥ 8.0lbs ISO 4919 ≥ 30 Newtons AS/NZS 2111.15 >30 Newtons
Wear - Castor Chair	ISO 4918 r ≥ 2.4 BS-EN 985 r ≥ 2.4
Wear - Vetterman Drum	TWC-TM247/TWC-TM251/TWC-TM284 >3
Colour Fastness to Light	ISO 105-B02 ≥ 4 - 5 AS2001 1.4.21 ≥ 4 AATCC 16E ≥ 4
Colour Fastness to Rubbing and Crocking	AS/NZS2111.19.1 ≥ 4 ISO 105-X12 ≥ 4-5 AATCC 165 ≥ 4
Colour Fastness to Water	AS2001.4.21 ≥ 4 ISO105-E01 ≥ 4-5 AATCC 107 ≥ 4
Flammability - Radiant Panel	ISO 9239-1 B1 ASTM E648 Class 1
Flammability - Smoke density	ISO 9239-1 Density < 750 %.min ASTM E662 Density ≤ 450
Antistatic	BS ISO 6356 ≤ 2.0Kv AATCC 134 < 3000 Volts
Antimicrobial Treatment	AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days ASTME-2471 Complete Inhibition AATCC 171 Washed

<b>Generic Tests</b>	
Acoustic - Nylon	Absorption Coefficient - NRC $\geq$ 0.10
Dynamic Loading	ISO 2094 $\geq$ 85%
	AS/NZS 2111.2 < 12.5% loss
Green Carpet (VOC)	ASTM D5116 Accredited
Static Loading	ISO 015/3415 Thickness after 60 mins recovery >85%
	AS/NZS2111.13 < 6% Loss
Thermal Resistance	ASTM C518 R Value $\geq$ 0.5
<b>Environmental Specifications</b>	
Recycled Content %	55-70
Other Environmental Claims	<a href="#">View Environmental Accreditations</a>
Ingredients and Life Cycle Impacts	<a href="#">View our Environmental Product Declarations</a>
End of Life	Carpet to Carpet Recycling
Carbon Neutral Floors™	Standard
<b>Technical Information</b>	
Maintenance	<a href="#">View recommended Interface Maintenance guidelines online</a>
Reclamation	<a href="#">View details on our ReEntry™ Program</a>
Warranty	15 Year Standard Warranty