



Collection World Woven **Product** WW880 **Colour** 8112-006-000 Natural Loom

Installation Methods



Herringbone Ashlar

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer

Product Specifications

Product Number	8112
Product Construction	Tufted Textured Tip Sheared Loop
Yarn / Fibre	BCF Nylon Type 6 - 100% Recycled content
Yarn Manufacturer	Aquafil
Colour System	100% Solution Dyed
Soil/Stain Protection	Protekt ^{2®}
Preservative Protection	Intersept [®]
Tufted Pile Weight	26 oz/yd ² ±10% 880 g/m ² ±10%
Machine Gauge	Tapestry
Stitches	39.4/10cm 10/in
Pile Thickness	3.0 mm ± 0.5mm
Total Thickness	7.5 mm ± 0.5mm
Pile Density	7,563 oz/yd ³ ± 10%
Size Description	25cm X 1m
Backing Structure (Learn more)	GlasBac [®]

Performance Specifications

Area of Use	Commercial - Heavy Duty
ACCS	Commercial Extra Heavy Duty & Stairs
Stability - Delaminating	ISO2551 ≤ 0.1% AS/NZS 2111.16 ≥ 50 Newtons ASTM D3936 ≥ 2.5lbs/in
Stability - Dimensional Stability	ISO/PAS 17984 < 0.2% ISO 2551 ≤ 0.1% ISO 2551 ≤ 0.2%
Stability - Tuft Bind	ASTM D1335 ≥ 8.0lbs ISO 4919 ≥ 30 Newtons AS/NZS 2111.15 >30 Newtons
Wear - Castor Chair	ISO 4918 r ≥ 2.4 BS-EN 985 r ≥ 2.4
Colour Fastness to Light	ISO 105-B02 ≥ 4 - 5 AS2001 1.4.21 ≥ 4 AATCC 16E ≥ 4
Colour Fastness to Rubbing and Crocking	AATCC 165 ≥ 4 AS/NZS2111.19.1 ≥ 4 ISO 105-X12 ≥ 4-5
Colour Fastness to Water	ISO105-E01 ≥ 4-5 AS2001.4.21 ≥ 4 AATCC 107 ≥ 4
Flammability - Radiant Panel	ISO 9239-1 B1 ASTM E648 Class 1
Flammability - Smoke density	ASTM E662 Density ≤ 450 ISO 9239-1 Density < 750 %.min
Antistatic	BS ISO 6356 ≤ 2.0Kv AATCC 134 < 3000 Volts
Antimicrobial Treatment	ASTME-2471 Complete Inhibition AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days AATCC 171 Washed

Generic Tests	
Acoustic - Nylon	Absorption Coefficient - NRC \geq 0.10
Dynamic Loading	ISO 2094 \geq 85%
	AS/NZS 2111.2 < 12.5% loss
Green Carpet (VOC)	ISO 10580 Accredited
	ASTM D5116 Accredited
Static Loading	ISO 015/3415 Thickness after 60 mins recovery >85%
	AS/NZS2111.13 < 6% Loss
Thermal Resistance	ASTM C518 R Value \geq 0.5
Environmental Specifications	
Recycled Content %	55-70
Other Environmental Claims	View Environmental Accreditations
Ingredients and Life Cycle Impacts	View our Environmental Product Declarations
End of Life	Carpet to Carpet Recycling
Carbon Neutral Floors™	Standard
Technical Information	
Maintenance	View recommended Interface Maintenance guidelines online
Reclamation	View details on our ReEntry™ Program
Warranty	15 Year Standard Warranty