CONSEQUENCE 2.0

Effect / Part Two / React / Sequel / Spin Off / Upshot



Construction	Tufted, Luxury Textured Loop Pile					
Face Fibre	100% Nylon 6 including 40% ECONYL® made with 100% regenerated fibre					
Soil Release	StainSmart [®] for soil release, liquid repellence					
Finished Face Weight	915 g/m ²					
Gauge	47.2 / 10 cm					
Rows	47.9 / 10 cm					
Tuft Density	226,088 /m ²					
Finished Pile Height	5.6 mm					
Standard Backing	Comfort Plus® 90% Recycled Polyurethane cushion Available with TractionBack® on request					
Nominal Total Thickness	11.8 mm					
Tile Size	50 cm x 50 cm					
Nominal Total Weight	4630 g/m ²					
Tiles per Box	16 (4m²)					

PERFORMANCE

Flammability (Euroclassification EN13501:1-2002)	Class Cfl – s1
Flammability (Radiant Panel ASTM-E-648)	Class 1
Flammability (Hot Metal Nut BS4790)	Low Radius of Char
Use Classification (EN 1307)	Class 33 Heavy Commercial Use
Static Electricity (ISO 6356)	Pass ≤ 2.0 KV Permanent Conductive Fibre
Impact Sound (ISO 10140-3)	33 dB
Sound Absorption (ISO354)	0.3 (H) Class D
Alpha s values	125Hz 0.03, 250Hz 0.07, 500Hz 0.42, 1000Hz 0.26, 2000Hz 0.36, 4000Hz 0.45

ENVIRONMENTAL

40% regenerated content yarn (20% post consumer)

90% Recycled content cushion backing 23% Recycled content by total product weight (9% post consumer)

Manufactured in ISO14001 certifed location using electricity from renewable sources

GuT & CRI Green Label Plus certified for indoor air quality

Brick

Half Drop

EPD verfied - BRE certified

Monolithic

WARRANTIES

15 year wear warranty Lifetime Antistatic guarantee Latent Defects guarantee

CERTIFICATIONS								
GREEN LABEL	CARPETS TESTED	THIRD.FAATY VERIFIED ISO 14925 and EN 15064						
GREPL LUEL Caret Arbains Caret Arbains Caret Arbains Caret Arbains Careto			ECONYL® Made with 100% Regenerated Nylon			٩		
INSTALLATION			CE MARKING					
Part Two/Sequel	Effect/React	Spin Off/Upshot	3 DDP-0338-100401 EN 140412004	C _{fI} -s1	E1 HCHO		NPD	

Design Copyright - Milliken & Company. This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.