

# ALMANAC

---

## CONSTRUCTION

Production Method:	ISO 2424	Tufting 1/10 <sup>th</sup> Loop Pile
Primary Backing:	ISO 2424	Nonwoven Polyester
Secondary Backing:	ISO 2424	Bitumen with Glass Fibre
Pile Type:	ISO 2076	100% Polyamide 6
Yarn Brand:		Xentrys
Number of tufts:	ISO 1763	212,700 / m <sup>2</sup> ± 5%
Pile Height:	ISO 1766	2.5mm. ± 0.5mm
Total Thickness:	ISO 1766	5.5mm. ± 0.5mm
Pile Weight	ISO 1958	620gr./m <sup>2</sup> ± 5%
Total Weight:	ISO 8543	4110gr./m <sup>2</sup> ± 10%
Pile Dinsety:	ISO 1959	0.120gr./cm <sup>2</sup> ± 10%
Tile Size:	ISO 3018	50 x 50cm.
Colour Range:		9
Wear Resistance:	EN 1307	Class 33
Castor Chair Test:	EN 985/A	Pass
Permanent Antistatic:		Yes
Walk on Test:	EN 1815	< 2 kV
Pass by IBM/ICL:		Yes
Radiant Panel Test:	ISO13501	Cfl-S1
Hot Metal Nut:	BS4790	Low radius of effects of ignition

## FASTNESSES

Light Fastness:	ISO 105 B02	5-6
Water Fastness:	ISO 105 E01	4-5
Rub Fastness:	ISO 105 X 12	4-5

---

We reserve the right to amend the technical specifications.  
 Subject to slight colour and structural deviations.  
 Discount Carpet Tiles. Net Limited.