

# Polysafe™ Modena

Polysafe Modena PUR is a heavy-duty safety flooring featuring a subtle micro granite decoration, ideal where underfoot performance and good aesthetics are key considerations. Used in areas which are normally dry but where are risks of water spillage, Modena features carborundum-free safety particles to ensure full HSE Compliance and sustainable wet slip resistance. Typical use areas include circulation areas, receptions, hospital wards, classrooms and cafes as well as washrooms, bar serveries and changing rooms. For continually wet areas such as showers, please refer to our Polysafe Hydro, Hydro Evolve or Ultima ranges.



## PRODUCT SPECIFICATION



- The flooring shall be Polysafe Modena PUR, as manufactured by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC sheet flooring in 2.0mm thickness, with the following construction: circa 0.7mm clear PVC wear layer with aluminium oxide granules incorporated throughout the full thickness - to impart enhanced slip resistance, a fibreglass reinforced integral print layer and circa 1.30mm of PVC backing.
- The flooring shall feature a high quality, cross-linked polyurethane reinforcement to provide superior cleaning benefits, life cycle maintenance savings and optimum appearance retention.



- The flooring material shall fully conform with the European Norm for safety flooring - EN 13845.
- In respect of flamespread, the flooring shall be categorised as Class Bfl-S1 according to EN 13501-1. The flooring shall have been fully tested to ASTM E648 by an independent test house and have a Class 1 rating, making it suitable for use in institutional, commercial and public buildings.
- The flooring must have been fully tested by an independent test house to the RRL Pendulum Test (4S Rubber/Slider 96) and have results of  $\geq 36$  in the wet, with a surface roughness of  $Rz \geq 20\mu m$ , making it suitable for use in areas where enhanced slip resistance is required.
- The product must have been fully tested for abrasion resistance to EN 13845, passing the 50,000 cycles test and also meeting EN 660-2 Abrasion Group T.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN 1815. For specialist applications where there is a requirement to dissipate the electrostatic charge, see the Polyflor ESD product ranges.
- The flooring shall possess a valid Agrément certificate when laid in accordance with the instructions of Polyflor, with coved skirtings and welded joints.
- The flooring must be available in 2.0 metre width, to minimise the number of joints.
- The flooring is suitable for Use Area Classification 23/34/43, as defined in EN ISO 10874 (EN 685).
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 and obtain  $\geq 6$



- The flooring will achieve BRE Global Environmental A+ rating ENP 415 in major use areas such as education and healthcare. Refer to BRE Global Ratings on [www.greenbooklive.com](http://www.greenbooklive.com)
- Generic EN 15804 Environmental Product Declaration (EPD) available on request.
- The manufacturer should provide a facility to take back and recycle waste vinyl flooring material through the Recofloor scheme.
- The flooring shall be tested to and pass key independent, international standards for low VOC emissions.



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.



- A moisture test must be carried out to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed, as outlined by Polyflor.
- Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
- All joints must be welded to produce hygienic, continuous floors.
- Suitable for use with underfloor heating up to 27°C. See Polyflor Technical Information Manual for details.



- Polysafe safety flooring ranges have good resistance to dilute acids and alkalis, are compatible for use with the most commonly used alco-based hand gels and are suitable for steam cleaning on a periodic basis. Chemical resistance charts available on request. For information regarding handling and installation, adhesives, maintenance, applications, chemical resistance and product warranty, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email [tech@polyflor.com](mailto:tech@polyflor.com). The slip resistance across all Polysafe products is assured throughout the guaranteed life of the product, with strict adherence to HSE Guidelines.
- As with all Polysafe products, Polysafe Modena PUR should not have a polish applied. For best results, flooring must be reverse laid.
- The data presented is correct at the time of printing. For latest information, please visit our website [polyflor.com](http://polyflor.com).

